

AN 106:89180 HCA  
TI Silicon carbide-metal joint  
IN Kameda, Tsuneji; Tanaka, Shunichiro  
PA Toshiba Corp., Japan  
SO Jpn. Kokai Tokkyo Koho, 3 pp.  
CODEN: JKXXAF

DT Patent  
LA Japanese

FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
	-----	---	-----	-----	-----
PI	JP 61227972	A2	19861011	JP 1985-67533	19850330 <--
AB	SiC and Cu or Cu alloy is joined by an interlayer of .gtoreq.2 layers, of Ti, Ag, and/or Cu to form substrates for semiconductor circuits. The interlayer may contain a Ni or Ni-based inside layer. A sintered SiC plate was polished on a side and washed with Me2CO for joining. A Cu plate was washed with dil. HNO3. A layer Ag-28% Cu alloy, a layer of Ti, and a layer of Ag-28% Cu were laid successively on the polished ceramic surface, the Cu plate was placed on top, and the stack was heated at 1000.degree. and <100 g/cm2 in a 10-4 torr vacuum for 5 min. The obtained laminate had the Cu plate in compact joint with the SiC plate.				